



Polypropylene HG385MO

Description

HG385MO is a polypropylene homopolymer intended for injection moulding. This grade combines unique Borstar reactor design with Borealis Nucleation Technology (BNT) to produce highly-crystalline polypropylene. This product is characterized by excellent flow properties combined with a narrow molecular weight distribution well suited for low distortion products. This grade contains anti-static and slip additives, which result in short cycle time, good demoulding and low dust attraction.

Products moulded from this grade exhibit excellent dimension consistency combined with high stiffness.

CAS-No. 9003-07-0

Applications

Caps and closures Items requiring good antistatic properties

Special Features

High stiffness Excellent antistatic properties

Physical Properties

Property	Typical Value	Test Method
<small>Data should not be used for specification work</small>		
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	25 g/10min	ISO 1133
Flexural Modulus	1.700 MPa	ISO 178
Tensile Modulus (1 mm/min)	1.750 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	8 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	36 MPa	ISO 527-2
Heat Deflection Temperature (0,45 N/mm ²) ¹	108 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	3 kJ/m ²	ISO 179/1eA

¹ Measured on injection moulded specimens acc. to ISO 1873-2

Processing Techniques

HG385MO is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature	220 - 260 °C	
Holding pressure	200 - 500 bar	Minimum to avoid sink marks.
Mould temperature	10 - 30 °C	
Injection speed	As high as possible.	