

# Vistamaxx™ Performance Polymer 6902

## Propylene Elastomer

### Product Description

Vistamaxx™ 6902 is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology.

### Key Features

- Can be blended with PE, PP and other polymers, including styrenic block copolymers.
- Excellent adhesion to conventional and metallocene PP and PE.
- Good chemical resistance to aqueous systems and non-hydrocarbon based fluids.
- Enhanced flow characteristics while maintaining elasticity.
- RoHS compliant.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>Europe</li> <li>Latin America</li> </ul>	<ul style="list-style-type: none"> <li>North America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>Compounding</li> </ul>	<ul style="list-style-type: none"> <li>Hot Melt Adhesives</li> </ul>	<ul style="list-style-type: none"> <li>Polymer Modification</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Adhesives</li> </ul>	<ul style="list-style-type: none"> <li>Compounding</li> </ul>	
RoHS Compliance	<ul style="list-style-type: none"> <li>RoHS Compliant</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		
Revision Date	<ul style="list-style-type: none"> <li>02/28/2022</li> </ul>		

### Physical

	Typical Value (English)	Typical Value (SI)	Test Based On
Density <sup>2</sup> (73°F (23°C))	0.869 g/cm <sup>3</sup>	0.869 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	43 g/10 min	43 g/10 min	ExxonMobil Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	100 g/10 min	100 g/10 min	ExxonMobil Method
Ethylene Content	12 wt%	12 wt%	ExxonMobil Method

### Hardness

	Typical Value (English)	Typical Value (SI)	Test Based On
Durometer Hardness (Shore A)	76	76	ExxonMobil Method

### Mechanical

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100%	490 psi	3.4 MPa	ExxonMobil Method
Tensile Stress at 300%	520 psi	3.6 MPa	ExxonMobil Method
Tensile Strength at Break	> 1100 psi	> 7.6 MPa	ExxonMobil Method
Elongation at Break	> 900 %	> 900 %	ExxonMobil Method
Flexural Modulus - 1% Secant	5300 psi	37 MPa	ASTM D790B

### Elastomers

	Typical Value (English)	Typical Value (SI)	Test Based On
Tear Strength (Die C)	260 lbf/in	45.5 kN/m	ExxonMobil Method

### Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	147 °F	64.1 °C	ExxonMobil Method

### Additional Information

Please contact Customer Service for food law compliance information.

### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

## Vistamaxx™ Performance Polymer 6902

### Propylene Elastomer

#### Processing Statement

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

#### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Property specified in conventional unit of measure.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2023 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)