

Linear Low Density Polyethylene

LL2119B**PRODUCT DESCRIPTION**

LLDPE butene resin for general packaging application.

APPLICATIONS

Product used for general packaging, including stretch film.

TYPICAL PROPERTIES

Properties		Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)		2.0 - 2.1	g/10 min	ASTM D1238
Density		0.918 - 0.919	g/cm ³	ASTM D1505
Tensile Strength at Break	MD	3,950 - 4,050	psi	ASTM D882
	TD	3,050 - 3,150		
Elongation at Break	MD	690 - 710	%	ASTM D882
	TD	890 - 910		
Haze		13.0	%	ASTM D1003
Dart Drop Impact Strength, F50		105 - 115	g/mil	ASTM D1709A

ADDITIVE

Antiblock	NONE
Slip	NONE
Other	NONE