



PP REPSOL ISPLEN PP070G2M

REPSOL ISPLEN PP070G2M is a phthalate free medium fluidity polypropylene homopolymer, intended for injection moulding. It is characterised by good flow properties that enables to fill the mould easier. Articles manufactured with this grade have excellent chemical resistance, are easily decorated and can accept different colouring systems.

Applications

REPSOL ISPLEN PP070G2M is widely used for the production of consumer goods such us:

- Food containers and rigid packaging.
- Toys and small appliances.
- Caps and closures.

Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	MÉTHOD
General			
Melt flow rate (230°C/ 2,16 kg)	12	g/10 min	ISO 1133
Density at 23°C	905	kg/m ³	ISO 1183
Mechanical			
Flexural modulus of elasticity	1550	MPa	ISO 178
Charpy impact strength (23°C,notched)	2,5	kJ/m ²	ISO 179
Thermal			
HDT 0,45 MPa	85	°C	ISO 75
Others			
Shore Hardness	68	-	ISO 868

REPSOL ISPLEN PP070G2M complies with the European Directives regarding materials intended for contact with foodstuffs. The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

Storage

REPSOL ISPLEN PP070G2M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

December 2020