



Arak Petrochemical Company



ISO 9001:2000

Certificate No.: CH98/8032

ISO 14001:2004

Certificate No.: CH03/0112

OHSAS 18001:1999

Certificate No.: CH05/0675

Address:

No. 3, Taban St.
Vali-e-Asr Ave.
Tehran - IRAN

Tel:

(+98 21)82122700

Fax:

(+98 21)8867 4126-27

Web-site:

www.arpc.ir

E-mail:

Sales@arpc-ir.net

High Density Polyethylene

BL3

Typical properties	Test method (DIN)	Unit	Value
MFI@190°C, 5 kg	53735	gr/10min	1
Density	53479	gr/ml	0.954
Notched Impact Strength	53453	mj/mm ²	Min. 6.5
ESCR, plax (70°C, 0.5bar)	Hoechst HDPE 19	hr	Min. 2
Standard Yellow Index	6167	-	Max. 4

➤ Values shown are averages & are not to be considered as product specifications.

❖ Main application & Characteristics:

BL3 is a high density polyethylene grade with broad molecular weight distribution, suitable for blow moulding applications.

◆ Characteristics:

- High rigidity.
- Good flow ability.
- Good impact strength.
- Good stress cracking resistance.

◆ Typical applications are:

- Containers ranging from a few ml up to 10 litres.
- Sheets for thermoforming.

* BL3 is suitable for food contact.