

LDPE ALCUDIA[®] 2335FG

DESCRIPTION

ALCUDIA[®] 2335FG is a low density polyethylene grade, produced by high pressure autoclave technology, suitable for thin blown film or cast film applications. This material offers easy processability and good balance of mechanical and optical properties. It contains high concentration of slip (erucamide), antioxidant and antiblock additives.

TYPICAL APPLICATIONS

- Pouches with good slip and optical properties.
- Automatic packaging
- Thin shring films
- Bags for the textile industry

Recommended melt temperature range from 140 to 165°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
General			
Melt Flow Rate (190°C, 2.16kg)	3.5	g/10 min	ISO 1133
Density at 23°C	923	kg/m ³	ISO 1183
Film ⁽¹⁾			
Dart drop (F ₅₀)	70	g	ISO 7765-1
Tear resistance (Elmendorf) (MD/TD)	300 / 200	cN	ISO 6383-2
Tensile stress at break (MD/TD)	18 / 13	MPa	ISO 527-3
Elongation at break (MD/TD)	200 / 300	%	ISO 527-3
Coefficient of friction (Dynamic)	0.2	-	ISO 8295
Gloss (45°)	100	-	ASTM D-2457
Haze	8	%	ASTM D-1003
Other			
Vicat softening temperature (load 10 N)	90	°C	ISO 306

(1) 40 µm thickness film, blow up ratio 2.5:1

ALCUDIA[®] 2335FG complies with the European Directives regarding materials intended for contact with foodstuffs. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

STORAGE

ALCUDIA[®] 2335FG should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes which may have a negative influence on the processability and the properties of the transformed product.

November 2013